

Simulating DTUL (ASTM D 648) Experiments with the TMA 943 or TMA 2940.

Heat Deflection Temperature (HDT) and Deflection Temperature Under Load (DTUL) are equivalent terms that reflect the temperature at which a material subjected to a three-point bending load deforms to a pre-determined position. The actual force applied to the sample and the amount of deflection required depend upon the sample geometry. ASTM D648 defines a standard set of these parameters. However, alternative arrangements such as the TMA flexure probe configuration (Figure 1) can be used to simulate this ASTM method, using the procedure described below.



ASTM D648 defines DTUL as the temperature at which a precise strain (either 0.25mm deflection or 0.20% strain as defined by sample dimensions in the procedure*) occurs under a specific stress (either 455 or 1820 kPa). With the TMA, the loads (force) needed to achieve these stresses can be determined using equation (1).

$$F = \frac{2}{3} \frac{\text{Sbd}^2}{\text{L}}$$

where:

F = TMA Force (N)

S = Stress (MPa)

- = 0.455 MPa (66 psi) or 1.82 MPa (264 psi)
- b = Sample width (mm)
- d = Sample thickness (mm)
- L = Sample length = 5.08mm (as defined by the flexure probe geometry, see Figure 1)

(1)

The TMA deflection equivalent to the ASTM specified % strain can be determined using the relationship shown in equation (2).

$$D = \frac{rL^2}{6d}$$
(2)

where:

D = TMA dimension change at center span (mm) r = Sample strain = 0.0020 or 0.20%*

*[Sample strain computed based on sample dimensions and deflection change defined by ASTM D648, namely, D=0.25mm, L=100mm, and d=13mm.]

TMA Experimental Guidelines

- Thin samples (1 mm thick or less) are cut to appropriate dimensions (10 mm long x 3 mm wide).
- Samples are placed on the bending fixture and the knife-edged probe is lowered onto the sample with the predetermined force (F).
- The sample is heated at 2°C/minute until the required deformation is achieved as defined by equation (2).
- The temperature at the required deformation is recorded as the DTUL for the corresponding stress.
- An example of a DTUL experiment is shown in Figure 2 for Polyvinyl Chloride.



Reference: ASTM Standard Test Method D648.

For more information or to place an order, contact:

TA Instruments, Inc., 109 Lukens Drive, New Castle, DE 19720, Telephone: (302) 427-4000, Fax: (302) 427-4001
TA Instruments S.A.R.L., Paris, France, Telephone: 33-01-30489460, Fax: 33-01-30489451
TA Instruments N.V./S.A., Gent, Belgium, Telephone: 32-9-220-79-89, Fax: 32-9-220-83-21
TA Instruments GmbH, Alzenau, Germany, Telephone: 49-6023-30044, Fax: 49-6023-30823
TA Instruments, Ltd., Leatherhead, England, Telephone: 44-1-372-360363, Fax: 44-1-372-360135
TA Instruments Japan K.K., Tokyo, Japan, Telephone: 813-5434-2771, Fax: 813-5434-2770

Internet: http://www.tainst.com

TA Instruments Thermal Analysis & Rheology A Subsidiary of Waters Corporation